(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 3 February 2005 (03.02.2005)

(10) International Publication Number WO 2005/011027 A2

(51) International Patent Classification7: 4/62, 10/40

H01M 4/02,

(21) International Application Number:

PCT/JP2004/011007

(22) International Filing Date: 27 July 2004 (27.07.2004)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

28 July 2003 (28.07.2003) 2003-280904 JP US 60/493,058 7 August 2003 (07.08.2003) 2004-131813 JP 27 April 2004 (27.04.2004) 60/567,010 3 May 2004 (03.05.2004) US

- (71) Applicant (for all designated States except US): SHOWA DENKO K.K. [JP/JP]; 13-9, Shiba Daimon 1-chome, Minato-ku, Tokyo 105-8518 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): OHKUBO, Takashi [JP/JP]; c/o Corporate R & D Center, Showa Denko K.K.,, 1-1, Ohnodai 1-chome, Midori-Ku,, Chiba-shi, 267-0056 (JP). SUDOH, Akinori [JP/JP]; c/o Omachi Plant, Showa Denko K.K., 6850 Oaza Omachi, Omachi-Shi (JP). TAKEUCHI, Masataka [JP/JP]; c/o Corporate R & D Center Showa Denko K.K., 5-1 Okawacho, Kawasaki-Ku, Kawasaki-Shi, Kanagawa 210-0858 (JP).

- (74) Agent: OHIE, Kunihisa, (8108), Patent, Attorney; Ohie Patent Office, Selva-Ningyosho 6F, 14-6, Nihonbashi-Ningyocho, 2-chome, Chuo-Ku, Tokyo 103-0013 (JP).
- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

without international search report and to be republished upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



(57) Abstract: The invention relates to a high-density electrode, obtained by impregnating a high-density electrode which comprises an electrode active substance and carbon fiber having a fiber filament diameter of 1 to 1,000 nm and has a porosity of 25% or less, with a solid polymer electrolyte; and to a battery including the resultant (high-density) electrode. According to the invention, electrolytic solution permeability and electrolytic solution retainability, which are matters of importance in realizing a high-density electrode for achieving a battery having a high energy density, can be improved.



(19) World Intellectual Property Organization

International Bureau



(43) International Publication Date 3 February 2005 (03.02.2005)

PCT

(10) International Publication Number WO 2005/011027 A3

(51) International Patent Classification⁷: 4/62, 10/40, 4/02, 10/40

H01M 4/02,

(21) International Application Number:

PCT/JP2004/011007

(22) International Filing Date: 27 July 2004 (27.07.2004)

(25) Filing Language: English

(26) Publication Language: **English**

(30) Priority Data:

2003-280904 28 July 2003 (28.07.2003) ЛР 60/493,058 7 August 2003 (07.08.2003) US 2004-131813 27 April 2004 (27.04.2004) ТР 60/567,010 3 May 2004 (03.05.2004) US

- (71) Applicant (for all designated States except US): SHOWA DENKO K.K. [JP/JP]; 13-9, Shiba Daimon 1-chome, Minato-ku, Tokyo 105-8518 (JP).
- (72) Inventors; and
- (75) Inventors/Applicants (for US only): OHKUBO, Takashi [JP/JP]; c/o Corporate R & D Center, Showa Denko K.K., 1-1, Ohnodai 1-chome, Midori-Ku,, Chiba-shi, 267-0056 (JP). SUDOH, Akinori [JP/JP]; c/o Omachi Plant, Showa Denko K.K., 6850 Oaza Omachi, Omachi-Shi (JP). TAKEUCHI, Masataka [JP/JP]; c/o Corporate R & D Center Showa Denko K.K., 5-1 Okawacho, Kawasaki-Ku, Kawasaki-Shi, Kanagawa 210-0858 (JP).
- (74) Agent: OHIE, Kunihisa, (8108), Patent, Attorney; Ohie Patent Office, Selva-Ningyosho 6F, 14-6, Nihonbashi-Ningyocho, 2-chome, Chuo-Ku, Tokyo 103-0013 (JP).

- (81) Designated States (unless otherwise indicated, for every kind of national protection available): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of
- (88) Date of publication of the international search report: 30 June 2005

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.



(54) Title: HIGH DENSITY ELECTRODE AND BATTERY USING THE ELECTRODE

(57) Abstract: The invention relates to a high-density electrode, obtained by impregnating a high-density electrode which comprises an electrode active substance and carbon fiber having a fiber filament diameter of 1 to 1,000 nm and has a porosity of 25% or less, with a solid polymer electrolyte; and to a battery including the resultant (high-density) electrode. According to the invention, electrolytic solution permeability and electrolytic solution retainability, which are matters of importance in realizing a high-density electrode for achieving a battery having a high energy density, can be improved.